

**5.9.4.1.2 TENSION STRESSES**

Temporary tensile stresses in prestress concrete before losses in all areas shall be limited to:

$$0.0948\sqrt{f'ci} \leq 0.2ksi$$

Reinforcing bars shall not be used to resist the tensile force in the concrete.